

### Description

Matrix FC is a high performance, fast cure, single component polyurethane adhesive/Sealant

Matrix FC exhibits exceptional adhesion capabilities and is suitable for a wide range of industrial and automotive adhesion applications for internal and external uses.

### Features

- Fast tack free time and cure speed
- Very high bond strength
- Excellent adhesion and sealing properties
- Good chemical resistance
- Excellent water resistance
- Paintable
- May be used in contact with both sea and fresh water
- One component, no mixing required
- Excellent resistance to weathering and aging
- Exceptional noise vibration and impact dampening characteristics
- Internal and external application
- Excellent acoustic properties
- Slump resistant
- Resistant to fungal attack

### Recommended Uses

- Automotive structural adhesive in bus, truck and industrial vehicle assembly.
- Marine commercial and pleasure craft
- Air-conditioning and refrigeration industrial and commercial applications
- Metal working, joining and sealing metal panels storage vessels, heavy shipping container vessels requiring sealing or panel installation
- General industrial and maintenance.
- For bonding sheet metal, aluminium, stainless steel, ABS, GRP, injection moulding PU and PVC as well as timber.
- Mining applications where sealing of cavities (joints) and adhering panels.

### Coverage

The coverage below is approximate and is dependant on substrate conditions.

Pack Size	Lineal meters 3mm bead	Lineal meters 6mm bead	Lineal meters 20mm bead
365gm cartridge	43	10	2.3
720gm sausage	81	19	4.4



### Application Instructions

#### Surface Preparation

Clean all surfaces by removing foreign matter and contaminants such as oil, dust, grease, frost, water, surface dirt, old sealants and any protective coating. Porous substrates should be cleaned by grinding saw cutting or blast cleaning (sand or water). Dust, loose particles, etc should be blown out of joints with oil free compressed air or vacuum cleaned. Non porous and plastic surfaces should be cleaned by solvent or mechanical means. Cleaning solvents should not be allowed to air dry or evaporate without being wiped with a clean, dry cloth.

#### Priming Porous Substrates

- Absorbent or porous substrates will allow a bead of water to easily soak into and wet out the surface of the substrate.
- For maximum performance on porous surfaces and, in all periodically immersed and submerged applications, use **Bostik N49 Primer**.
- Porous substrates not subject to immersion or ponded water, e.g. vertical expansion joints in concrete or masonry structures, do not require priming if clean, dry and uncontaminated.

#### Priming Non Porous Substrates

- **Bostik N40 Primer** is recommended for non-porous plastic and metal substrates.
- Prime all plastics and metallic non-porous substrates with **Bostik N40 Primer** using the two-cloth method described below.
- E.g. UPVC outlets and pipe work: brass, copper fittings, stainless steel trays and flashings

#### Two Cloth Method – N40 Primer Application

- Dampen a clean and dry cloth with **Bostik N40 Primer** and spread evenly over the non-porous substrate using a cleaning/rubbing action.
- With a second clean and dry cloth, immediately wipe all primer residues off with a buffing action.
- Allow the substrate to dry for a minimum of 5 minutes before installing Bostik **Matrix FC**.
- Do not leave the primer longer than 4 hours before applying sealant/adhesive.
- Re-prime if 4 hours has elapsed without applying sealant/adhesive
- Clean and re-prime if the primed surface is contaminated before **Bostik Matrix FC** is applied.

Pierce the membrane completely from the top of the cartridge and screw on the supplied nozzle. (Having previously cut this to give the required angle and bead size.)

Place the cartridge in a suitable Bostik extrusion skeleton type gun and press the trigger.

For sausages, a barrel gun is required, which is also available from Bostik. Clip/cut the end of the sausage and place complete sausage with pierced end located at the top of the nozzle. Screw top of nozzle and housing on barrel of gun. Using the trigger on the gun, extrude product from the sausage. To stop product flow, depress using the thumb on to catch plate mechanism located at the very rear of the gun, directly above the trigger.

Apply a bead of Matrix FC to one surface to be bonded. Bring the opposite surface into contact with the wet adhesive and compress to give a glue line thickness of 1 to 2mm. Clamp together until cured, at least 8 hours at 20° to 25°C.

#### Precautions

- May be used for joints subjected to constant immersion in water, provided Matrix FC has achieved full cure (7 days at 20°C) prior to immersion.
- Do not apply Bostik Matrix FC to any material containing bitumen. **Do not** allow bitumen to contact Bostik Matrix FC.

- May be painted over after full cure however, Matrix FC is not recommended for use under solvent-based coatings such as gloss enamels. A field test is recommended to ensure compatibility.
- Matrix FC should not be applied with wet tooling techniques. Using solvents, water, detergent or soap solutions is not recommended.
- Matrix FC should not be applied to surfaces with special protective or cosmetic coatings such as mirrors, reflective glass surfaces coated with Teflon without prior consultation with a Bostik representative..
- Avoid contact with water prior to initial cure. Matrix FC can be affected by water before or during cure.
- Do not apply, store or cure Matrix FC in areas where unusually high humidity or free water are present during the application or initial cure.
- Matrix FC should not be used in highly chlorinated areas such as swimming pools, spas etc without prior consultation with a Bostik representative.
- Do not apply at temperatures below 5°C and temperatures above 35°C
- Ensure cartridge temperature and contents are between 10°C and 30°C prior to applications. This will eliminate curing problems.
- Ensure Bostik Primer Selection Guide is referred to prior to application of Matrix FC.
- Do not use alcohol based cleaners to prepare surfaces or to clean up uncured adhesive. Alcohols will inhibit the adhesives cure.
- Take care when using Matrix FC on 'colour bonded' or powder coated steel or aluminium. Always conduct tests to ensure adequate adhesion on the particular grade of metal to be used.
- 
- As all substrates and conditions are different, it is strongly recommended that the applicator or end user conducts their own tests and ensure the product meets their own end use requirements.

### Paintability

- Matrix FC can be painted after fully curing by most conventional coating systems including epoxy resins and acrylic coatings. Coatings containing high solvent contents such as gloss enamels or high oil-based undercoats may cause the surface of Matrix FC to react resulting in a tacky soft surface.
- A field test is recommended to ensure compatibility.
- To obtain best appearance and performance the paint must approximate the elongation capabilities of Matrix FC. Thin or watered down coatings will surface craze very quickly upon movement.
- For sections less than 3mm thickness Matrix FC may be painted in over 24 hours.
- For sections greater than 3mm thickness Matrix FC may be painted 48 hours after application.
- High build coatings with some elastomeric ability such as quality acrylic emulsions have the capability to absorb low movement without significant distortion of the paint film.
- For additional information contact a Bostik representative.

### Properties

Typical properties after seven days cure at 25°C 50% RH

Appearance	Non-sag smooth Thixotropic paste	Tack-free time (skin time)	45 Minutes
Stain and colour change	None	Full cure	7 days at 25° C and 50% RM
Chemical type	Polyurethane component Moisture cure) (1	Service temperature	-40°C to + 80°C continuous

Chemical resistance	Good	Application temperature	+ 5°C to + 35°C
Specific Gravity	1.23 ± 0.03	Elongation modules at 100%	> 450%
Shore Hardness A	Approx. 45 - 50	Colour	Black, grey and white
Tensile strength at break	> 2.5 N/mm <sup>2</sup>	Chemical resistance	Resistant to dilute acids & alkalis, some solvents, intermittent contact with diesel and petroleum
Tool working time	30 Minutes	Potable water approval	AS4020

Matrix FC is tested to International and Australian Standards AS 1527, ASTM D412, ASTM C719 and ASTM C793

### Storage & Shelf Life

Store in a cool, dry place, out of direct sunlight. Storage areas must be well ventilated and comply with Local, State and Federal regulations. For maximum shelf life, store between 5° and 20°C.

Shelf life is up to 12 months when stored in original, unopened containers, under the above conditions.

### Health & Safety

Please refer to the Material Safety Data Sheet which is available on request.

### Clean Up

Clean up uncured material and equipment immediately after use using **Bostik Handy Wipes**. Cured material can be removed by mechanical means only.

### Packaging

Matrix FC is available in 365gm (300ml) cartridges, 720gm (600ml) sausages and 360gm (300ml) sausages (on request)

### Product Details

Item Number	Size	Colour	Pack Quantity
258946	365gm (305ml) Cartridge	Black	20
258911	365gm (305ml) Cartridge	Grey	20
258938	365gm (305ml) Cartridge	White	20
258970	720gm (600ml) Sausage	Black	20
258954	720gm (600ml) Sausage	Grey	20
258962	720gm (600ml) Sausage	White	20
259241	360gm (300ml) Sausage	Black	20
259276	360gm (300ml) Sausage	Grey	20
259268	360gm (300ml) Sausage	White	20

The representations and recommendations regarding the products are based on tests which we believe to be reliable. However, no guarantee of their accuracy can be made because of the great range of field conditions and variations encountered in raw materials, manufacturing equipment and methods. Thus, the products are sold with a limited warranty only, and on the condition that purchasers will make their own tests to determine the suitability of the product for their particular purposes. Under no circumstances will Bostik Australia Pty Ltd be liable to anyone except for replacement of the products or refund of the purchase price.

**ALL SALES ARE EXPRESSLY LIMITED TO THE TERMS AND CONDITIONS OF SALE OF  
BOSTIK AUSTRALIA PTY LTD**

Head Office            Bostik Australia Pty Ltd, 51-71 High Street, Thomastown Vic 3074  
                                 A.B.N. 79 003 893 838  
                                 Phone: (03) 9279 9333            Fax: (03) 9261 4744  
                                 Phone Industrial:                Toll free 1300 560 799



Quality  
ISO 9001  
SAI GLOBAL  
Quality endorsed ISO9001 (Thomastown site)  
TS16949 (Automotive).

Product:            Matrix FC  
Issue Date:        September 2014  
Issue No.:            7  
Author:              Dean Toohey  
Division:            Industrial Adhesives  
Total Pages:        5